



Common Spring Materials

Common Names

	Specification	Uses	Maximum Operating Temperature		Corrosion Resistance	Electrical Conductivity % IACS	Minimum Tensile Strength (KSI)
			F	C			
Carbon Steels							
Music Wire	ASTM A228	Most common carbon spring wire	250	120	Poor	7	230 - 399
Hard Drawn	ASTM A227	Used where economy is important / volume high	250	120	Poor	7	147 - 283
Oil Temper Wire	ASTM A229	More common in heavier springs	300	150	Poor	7	165 - 293

Alloy Steels

Chrome Vanadium	ASTM A231	For shock loading applications	425	220	Poor	7	190 - 300
Chrome Silicon	ASTM A877	For high temperatures and high stress	475	245	Poor	5	235 - 300

Stainless Steels

Type 302	ASTM A313 (302)	Most common spring temper stainless	500	260	Good	2	125 - 325
Type 316	ASTM A313 (316)	Higher corrosion resistance than 302	500	260	Better	2	110 - 245
17-7PH	ASTM A313 (631)	Higher tensile strength than 302 or 316	600	315	Good	2	235 - 335

Copper Based Alloys

Phosphor Bronze	B159	Most common copper based alloy	200	93	Better	15	105 - 145
Beryllium Copper	B197	Higher tensile strength and conductivity	400	204	Better	21	150 - 230
Brass	B134	Lower cost and lower tensile strength	200	93	Good	17	120

Nickel Base Alloys

Inconel® 600	ASTM B166	Elevated temperature, corrosion resistance	640	340	Best	1.5	170 - 230
Inconel® X-750	AMS 5699	Highest Temperatures, corrosion resistance	1020	550	Best	1	190 - 230 (Spg T)
Monel® 400	ASTM B164	Excellent corrosion resistance	450	230	Best	3.5	145 - 180
Monel® K500	QQN-281 C1	Excellent corrosion resistance, High/Low temp	500	260	Best	3	160 - 200
Hastloy® C276	ASTM B574	Excellent corrosion resistance, High Temperature	750	400	Best	1	205 - 250

The information and data presented herein are typical or average values and are not guarantee of maximum or minimum values.

Applications specifically suggested for material described herein are made solely for the purpose of illustration to enable the reader to make his own evaluation and are not intended as warranties, either express or implied, of fitness for these or other purposes.

Inconel and Monel are registered trademarks of International Nickel Company. Hasteloy is a registered trademark of Haynes International.